

TECHNICAL DATA SHEET

TDS: CVW138

ACRYLIC FLOOR PAINT

115/W138

DESCRIPTION:

A water thinned floor paint. Easy to apply and fast drying with low odour.

RECOMMENDED USE:

Can be used on tarmac as well as concrete, asphalt, wood, walls, window ledges, bricks or metals. Based on water as a solvent. For foot and light truck traffic use. Can be used inside or outside.

AVAILABILITY:

1 litre, 2,5 litre, 5 litre

FINISH:

Semi Gloss

COLOUR:

White, Black, Tile Red, Flint Grey, Forest Green

TYPICAL S.G. (SPECIFIC GRAVITY):

1.05 to 1.2 @ 20 °C

VOLUME SOLIDS:

32 to 35%

WET FILM THICKNESS W.F.T

90 microns

DRY FILM THICKNESS D.F.T

30 to 35 microns

EXPECTED SPREADING RATE:

11 sq.m / litre

@ 30 microns D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

2.5 Poise @ 25 °C

FLASH POINT:

Non-flammable

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 1.5 hours @ 20 °C

Hard dry: 6 hours @ 20 °C

Full hardness: 3 to 5 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

6 hours

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

Max 91 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application Do not apply below 7 °C. restrictions

Method: Brush or Roller

Thinner Clean Water
(Max vol): (5%)

Nozzle size: N/A

Nozzle N/A
pressure:

Cleaning Water
solvent:

Recoat 6 hours
interval:

SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR

Email: info@coo-var.co.uk

www.coo-var.co.uk

ACRYLIC FLOOR PAINT**115/W138****REMARKS:**

Concrete - power floated, granolithic and smooth surfaces should be roughened first to provide a good "key" for the paint. This can be done mechanically by abrading or blasting, or chemically, using Coo-Var Acid Etch. These processes will have the advantage in addition to preparing the surface of also removing dirt and laitance. New concrete must be allowed to cure thoroughly which can take up to 3 months.

Other surfaces have to be prepared and primed with the suitable primer for that substrate.

Existing painted surfaces - Surfaces should be cleaned, degreased and sanded to ensure an adequate "key" is produced. Remove all loose and flaking material and treat bare areas as new substrate and prepare accordingly.

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

As dictated by normal good painting practice.

Do not apply if the temperature is likely to drop below 7 °C during application or during the drying process.

In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Apply direct to wood, Coo-Var All Metals Primer on Metal, Coo-Var Acrylic Floor Paint thinned 5% with clean water on all other unpainted surfaces.

SUBSEQUENT COAT:

Coo-Var Acrylic Floor Paint

HEALTH AND SAFETY:

See safety data sheet - SDS 10623

ISSUED:

20 May 2010

REVISION:

1

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-var

Email: info@coo-var.co.uk

www.coo-var.co.uk