



TECHNICAL DATA SHEET

TEAMAC FARM OXIDE PAINT

TDS: TMG150 430/G150

DESCRIPTION:

Teamac Farm Oxide Paint is a general purpose, versatile product giving economical protection and decoration.

RECOMMENDED USE:

Teamac Farm Oxide Paint can be used for the maintenance of structural steel, cladding etc., when applied to properley prepared surfaces. May be used coat on coat. Dries to a durable finish.

AVAILABILITY:

5 litre, 20 litre

FINISH:

See Remarks

COLOUR:

Red, Grey, Green, Black

TYPICAL S.G. (SPECIFIC GRAVITY):

1.17 to 1.31 @ 20 °C

VOLUME SOLIDS:

50 to 52.6

WET FILM THICKNESS W.F.T

75

microns

DRY FILM THICKNESS D.F.T

35 to 40 microns

EXPECTED SPREADING RATE:

13 sq.m / litre

@ 35 microns D.F.T.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

FLASH POINT:

4.5 Poise @ 25 °C

Above 32		°C (closed cup)
DRYING TIME: @ RECOMMENDED D.F.T		
Touch dry:	5	hours @ 20 °C

Hard dry: 24 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

12 hours or overnight

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

Max g / litre 394.04

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A restrictions

Method: Brush or Roller **Airless Spray**

Thinner Thinners 14 (Max vol): (10%)

Thinners 14 (10%)

Nozzle size: N/A

Nozzle 1800 to 2000 psi pressure:

Cleaning Thinners 14 solvent:

Recoat 12 hours or interval: overnight

For further advice contact Teamac Technical Services on +44(0)1482 320194 The physical constants are subject to normal manufacturing tolerances. "COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

TEAMAC

Lockwood Street, Hull HU2 0HN Tel.: +44(0)1482 320194. Fax: +44(0)1482 219266 Email: info@teamac.co.uk www.teamac.co.uk

TECHNICAL DATA SHEET

TEAMAC FARM OXIDE PAINT

SURFACE PREPARATION:

Ensure all surfaces are clean, dry and free from grease, oil and any other contaminates. Bare steel should be free from dust, rust and scale. Blast cleaning to SA 2½ is recommended. If blast cleaning is impractical, mechanical cleaning should be employed as hand cleaning does not clean the steel to the required degree. Any oil or grease should be removed with Coo-Var Degreaser before de-rusting. Where blast cleaning is carried out after assembly, special attention must be paid to edges, corners, nuts, bolts, welds etc. Welds should, if necessary be ground and all weld spatter, slag etc. must be removed.

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

As dictated by normal good painting practice. Care must be taken during application that the temperature is above the dew point to avoid any contamination. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Can be applied directly to prepared iron or steel. For greater protection prime with Teamac Zinc Phosphate Metal Primer.

SUBSEQUENT COAT:

Teamac Farm Oxide Paint

REMARKS:

Red has a Gloss Finish, all other colours are a semi-gloss finish.

ISSUED:

13 September 2017

REVISION:

1

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specificaton. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 320194.

TDS: TMG150

430/G150

HEALTH AND SAFETY:

See safety data sheet - Red, Grey and Green - SDS 10579, Black - SDS 10599

For further advice contact Teamac Technical Services on +44(0)1482 320194 The physical constants are subject to normal manufacturing tolerances. **"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

TEAMAC

Lockwood Street, Hull HU2 0HN Tel.: +44(0)1482 320194. Fax: +44(0)1482 219266 Email: info@teamac.co.uk www.teamac.co.uk